



INTERNATIONAL APPLICATION PUBLISHED UNDER THE PATENT COOPERATION TREATY (PCT)

(51) International Patent Classification ⁷ : H01M 4/42, C22C 1/04, B22F 9/10	A1	(11) International Publication Number: WO 00/48260 (43) International Publication Date: 17 August 2000 (17.08.00)
(21) International Application Number: PCT/EP00/00932 (22) International Filing Date: 3 February 2000 (03.02.00) (30) Priority Data: 99200353.3 9 February 1999 (09.02.99) EP (71) Applicant (for all designated States except US): N.V. UNION MINIERE S.A. [BE/BE]; 31, rue du Marais, B-1000 Brussels (BE). (72) Inventors; and (75) Inventors/Applicants (for US only): STRAUVEN, Yvan [BE/BE]; Hayenhoeck 29, B-3910 Neerpelt (BE). GAY, Bruno [BE/BE]; 265, rue de Noyer, B-1000 Bruxelles (BE). (74) Common Representative: N.V. UNION MINIERE S.A.; Knockaert, Guy, 7, Kasteelstraat, B-2250 Olen (BE).		(81) Designated States: AE, AL, AM, AT, AU, AZ, BA, BB, BG, BR, BY, CA, CH, CN, CR, CU, CZ, DE, DK, DM, EE, ES, FI, GB, GD, GE, GH, GM, HR, HU, ID, IL, IN, IS, JP, KE, KG, KP, KR, KZ, LC, LK, LR, LS, LT, LU, LV, MA, MD, MG, MK, MN, MW, MX, NO, NZ, PL, PT, RO, RU, SD, SE, SG, SI, SK, SL, TJ, TM, TR, TT, TZ, UA, UG, US, UZ, VN, YU, ZA, ZW, ARIPO patent (GH, GM, KE, LS, MW, SD, SL, SZ, TZ, UG, ZW), Eurasian patent (AM, AZ, BY, KG, KZ, MD, RU, TJ, TM), European patent (AT, BE, CH, CY, DE, DK, ES, FI, FR, GB, GR, IE, IT, LU, MC, NL, PT, SE), OAPI patent (BF, BJ, CF, CG, CI, CM, GA, GN, GW, ML, MR, NE, SN, TD, TG). Published <i>With international search report.</i> <i>Before the expiration of the time limit for amending the claims and to be republished in the event of the receipt of amendments.</i>
(54) Title: CENTRIFUGALLY ATOMIZED ZINC ALLOY POWDER FOR ALKALINE BATTERIES (57) Abstract <p>This invention relates to centrifugal atomized zinc alloy powders for alkaline batteries consisting of (a) 0.005–2 % by weight of indium, and 0.005–0.2 % by weight of either one of Al and Bi, or (b) 0.005–2 % by weight of indium, and 0.005–0.2 % by weight of Bi, and 0.001–0.5 % of either one or both of Al and Ca, or (c) 0.005–2 % by weight of either one or both of Bi and Al, and 0–0.5 % by weight of Pb, the remainder being zinc. The powder is obtained by centrifugal atomisation in a protective atmosphere, where the oxygen content is less than 4 % by volume. The resistance to corrosion in the electrolyte of the battery, especially after partial discharge, is markedly better than when the same alloys are prepared by the traditional production process. The capacity of batteries containing these powders is very good.</p>		

FOR THE PURPOSES OF INFORMATION ONLY

Codes used to identify States party to the PCT on the front pages of pamphlets publishing international applications under the PCT.

AL	Albania	ES	Spain	LS	Lesotho	SI	Slovenia
AM	Armenia	FI	Finland	LT	Lithuania	SK	Slovakia
AT	Austria	FR	France	LU	Luxembourg	SN	Senegal
AU	Australia	GA	Gabon	LV	Latvia	SZ	Swaziland
AZ	Azerbaijan	GB	United Kingdom	MC	Monaco	TD	Chad
BA	Bosnia and Herzegovina	GE	Georgia	MD	Republic of Moldova	TG	Togo
BB	Barbados	GH	Ghana	MG	Madagascar	TJ	Tajikistan
BE	Belgium	GN	Guinea	MK	The former Yugoslav Republic of Macedonia	TM	Turkmenistan
BF	Burkina Faso	GR	Greece	ML	Mali	TR	Turkey
BG	Bulgaria	HU	Hungary	MN	Mongolia	TT	Trinidad and Tobago
BJ	Benin	IE	Ireland	MR	Mauritania	UA	Ukraine
BR	Brazil	IL	Israel	MW	Malawi	UG	Uganda
BY	Belarus	IS	Iceland	MX	Mexico	US	United States of America
CA	Canada	IT	Italy	NE	Niger	UZ	Uzbekistan
CF	Central African Republic	JP	Japan	NL	Netherlands	VN	Viet Nam
CG	Congo	KE	Kenya	NO	Norway	YU	Yugoslavia
CH	Switzerland	KG	Kyrgyzstan	NZ	New Zealand	ZW	Zimbabwe
CI	Côte d'Ivoire	KP	Democratic People's Republic of Korea	PL	Poland		
CM	Cameroon	KR	Republic of Korea	PT	Portugal		
CN	China	KZ	Kazakhstan	RO	Romania		
CU	Cuba	LC	Saint Lucia	RU	Russian Federation		
CZ	Czech Republic	LI	Liechtenstein	SD	Sudan		
DE	Germany	LK	Sri Lanka	SE	Sweden		
DK	Denmark	LR	Liberia	SG	Singapore		
EE	Estonia						

CENTRIFUGALLY ATOMIZED ZINC ALLOY POWDER FOR ALKALINE BATTERIES

This invention relates to centrifugal atomized zinc alloy powders for
5 alkaline batteries.

Zinc alloy powders are used as an ingredient of the anode active material
of alkaline batteries. Zinc alloy powders containing one or more elements
selected from In, Bi, Al, Ca and Pb, are known from US 5,082,622 and
10 WO 94/19502. Such alloys are normally prepared by traditional powder
manufacturing techniques, such as allowing the molten alloy to flow away in a
jet of compressed air. The use of a protective atmosphere in such gas jet
atomisation process is possible, but quite expensive because of the high flow
rate needed. Powders which are manufactured by compressed air atomisation
15 do not always have an acceptable resistance to corrosion in the electrolyte of
the battery, especially after partial discharge of the latter. A well-known way
of dealing with a low resistance to corrosion is by adding certain amounts of
organic or inorganic products. An example of an organic product is
polyethylene glycol. However this procedure also has some disadvantages,
20 e.g. the battery capacity could be decreased.

Centrifugal atomisation is a method in which molten metal is poured
from a nozzle on a high velocity rotating plate, a cup or a disk with a
predetermined shape whereby the metal is disintegrated by centrifugal force.
The above cited documents merely mention that the powders can also be
25 manufactured by centrifugal atomisation without specifying any working
condition. In these documents the particular effects of using centrifugal
atomized powders are not investigated.

According to the invention, a zinc alloy powder prepared by centrifugal
30 atomisation in a protective atmosphere with a reduced oxygen content has a
better resistance to corrosion than a powder prepared by atomisation in a
stream of air. Moreover, unacceptably low corrosion resistance values of some
of the above mentioned zinc alloy powders prepared by atomisation in air are
turned into acceptable values when the same alloys are prepared by
35 centrifugal atomisation in said protective atmosphere. The use of organic and
inorganic corrosion inhibitors can be limited, or even eliminated. The capacity
of batteries containing powders according to the invention is good. The

production method is economically sound, because the consumption of gas in the protective atmosphere is very low.

The alloy powder of the invention consists of either

- 5
- (a) 0.005-2 %, and preferably 0.01-2 % by weight of indium; and 0.005-0.2 %, preferably 0.01-0.2 % by weight of either one of Al and Bi, or
 - (b) 0.005-2 % by weight of indium; and 0.005-0.2%, preferably 0.01-0.2 % by weight of Bi; and 0.001-0.5%, preferably 0.003-0.5 % of either one or both of Al
 - 10 and Ca, or
 - (c) 0.005-2%, and preferably 0.01-2 % by weight of either one or both of Bi and Al,

and in each case 0-0.5 % by weight of Pb, the remainder being zinc.

- 15 By zinc is meant here and in the following thermally or electrolytically refined zinc (Special High Grade). In SHG zinc, the Pb content is normally limited to less than 30 ppm. For economical reasons the indium content can be limited to 5000 ppm, or even to 1000 ppm.

- 20 The powder is prepared by centrifugal atomisation, characterized in that this atomising process is performed in a protective atmosphere, mainly consisting of inert gasses, which controls the oxidation. More particularly, the oxygen content in the atmosphere is less than 4% by volume.

- 25 In order to prevent excessive oxidation, the oxygen content is limited to 4%, and preferably less than or equal to 3.5%. On the other hand, a minimum amount of oxygen can be useful to control the shape of the solidified droplets. Also, too low oxygen contents imply a reduction of the capacity of the battery. For these reasons the oxygen content is preferably greater than 0%, and especially greater than or equal to 0.2%.

- 30 The rotating disk of the atomizer is made out of materials like alumina, carbon or fused silica, which can also be coated to prevent oxidation or occurrence of accretion.

- 35 Another object of the invention is a process to manufacture zinc alloy powders comprising the step of centrifugally atomising the zinc alloys mentioned above and characterized in that the centrifugal atomising process is performed in a protective atmosphere, where the oxygen content is less than 4% by volume, and preferably greater than 0 % by volume. Most preferably the oxygen content is between 0.2 % and 3.5 % by volume.

The applicant has found that when the powders described previously are prepared by a centrifugal atomising process in the above described protective atmosphere, they are consistently showing a better resistance to corrosion in the electrolyte of the battery, after partial discharge of the latter, compared to powders with identical compositions and prepared by air jet atomisation. The resistance to corrosion and the capacity of the powders according to the compositions of the invention, and prepared by centrifugal atomisation, are all recommendable for practical use in alkaline batteries. In a further experiment it is shown that the capacity of a battery using powders prepared by centrifugal atomisation according to the invention is better than when powders are used prepared by gas jet atomisation in a protected atmosphere with the same oxygen content.

In case the desired powder contains additives which can be cemented (for instance In), then another way to produce the powder consists in preparing a powder with the additives which cannot be cemented and optionally with a part of the additives which can be cemented according to the above mentioned method of centrifugal atomisation and making an anode from the thus obtained powder. That anode is introduced in the battery and the additives which can be cemented, are either added to the electrolyte of the battery, from which they cement on the powder of the anode, or they are cemented before the introduction in the battery. It is also possible to obtain powders for alkaline batteries by mixing a powder with a given composition and produced in a traditional way, such as atomisation in a stream of air, with a powder which was prepared by centrifugal atomisation in a protective atmosphere, according to the invention.

This invention relates not only to a powder such as it is introduced in the battery, but also to a powder such as it is present in the battery, and which consists entirely or partly of powder prepared by centrifugal atomisation, the remainder being prepared by traditional powder manufacturing techniques.

The powder is suitable for use in any type of battery, such as LR6, LR14, LR20.

Here, the following should be noted: Centrifugal atomized zinc alloy powders are mentioned in "*Atomization of melts for Powder Production and Spray Deposition*", by A.J. Yule and J. J. Dunkley ; Clarendon Press, Oxford; 1994; pp. 223-224. According to Yule, centrifugal atomisation is used as it gives a

very closely controlled particle size distribution, which renders the powder production more economical. It is also possible, by control of the atmosphere inside the atomizer, to control the particle shape and hence the surface area and apparent density of the powder, both of which are significant for battery applications. This publication however does not mention which alloys can be exploited beneficially for this application, and neither is described what the controlled atmosphere inside the atomizer should be. Also it does not describe if and in what way the process of centrifugal atomisation has an influence on the characteristics of the batteries prepared with these powders.

10

Experiment 1

In an example of producing the powder of the invention, the powders are prepared by adding the desired quantities of the alloying elements to molten zinc, which is homogenized by stirring at elevated temperature. The process of centrifugal atomisation is carried out as follows: about 150 kg of alloyed zinc is melted in a protective atmosphere at 480°C and poured on a rotating disk. The rotating disk is made of carbon, and placed 25 mm below the ejecting nozzle concentrically, 1.5 m above the bottom at the centre of the atomising chamber. The atomising chamber is filled with nitrogen and 0.4% to 3.3% of oxygen (see Table 1). The rotation speed is about 5000 rpm, the diameter of the disk is 170 mm and the flow rate of molten metal is about 530 kg/hr.

With the alloy powders batteries of the LR14-type are produced. These batteries are discharged over 2 Ohm for 1 hr or for 4 1/2 hrs. Subsequently one determines the quantity of hydrogen which is evolved when the batteries are maintained for 7 days at 71°C. The resulting gas production is expressed as ml of gas per battery. Also the volume expansion of a partially discharged anode is measured after 24 hrs at 71°C, and the volume increase is expressed as a percentage of the original volume. This measuring technique is an out-of-cell test described in US 5,364,715. Both in cell and out-of-cell gassings are a measure for the gassing after partial discharge.

The results of these tests are compared with results on traditional air atomized powders with the same chemical composition. In the examples, all powders are sieved on 500 micron to take away the very course particles. The results of Experiment 1 are summarized in Table 1.

Table 1: experimental results of centrifugally atomised powders vs. powders atomised in a stream of air

Ex. No.	Alloy powder additives (ppm)				(*)	O ₂ % by Vol	Volume expansion (%)	Gassing after partial discharge 4 1/2 hrs, 2 Ohm (ml)	Gassing after partial discharge 1 hr, 2 Ohm (ml)
	In	Bi	Ca	Al					
(1)	150	230	-	-	C	0.4	3.4	4.63	1.95
(2)	500	100	-	100	C	0.4	1.7	2.07	1.5
(3)	200	180	-	70	C	0.4	3.6	3.67	1.7
(4)	250	250	150	-	C	0.4	3.1	3.57	1.37
(5)	-	250	-	-	C	0.4	6.5	8.05	3.12
(6)	2000	500	-	-	C	0.4	3.4	2.38	1.83
(7)	200	-	-	70	C	1.0	4.1	4.20	na
(8)	-	200	-	70	C	0.8	2.1	4.03	na
(9)	200	100	180	70	C	3.3	1.5	2.33	na
(10)	150	230	-	-	T	air	28.4	10.65	13.63
(11)	500	100	-	100	T	air	5.6	2.5	2.3
(12)	200	180	-	70	T	air	5.1	4	1.7
(13)	250	250	150	-	T	air	10.2	4.08	6.75
(14)	-	250	-	-	T	air	19.8	9.23	12.13
(15)	2000	500	-	-	T	air	41.9	12.7	19.58
(16)	200	-	-	70	T	air	43.6	19.53	na
(17)	-	200	-	70	T	air	4.5	6.13	na
(18)	200	100	180	70	T	air	2.4	4.07	na
(19)	500	5000	-	70	T	air	26.2	16.7	13.5
(20)	500	5000	-	70	C	0.4	30.1	13.5	6.37
(21)	600	-	-	-	T	air	87.6	52.63	(**)
(22)	600	-	-	-	C	0.4	42.1	25.07	22.43
(23)	900	-	-	-	C	0.4	25.9	21.38	15.9
(24)	40	40	-	-	C	0.4	28.5	11.63	8.57

5 (*): 'C': centrifugal atomized powder; 'T': powder preparation by traditional air jet atomisation

(**): Leakage occurred, which indicates that gassing was excessive and unacceptable.

na: not available

5 For the volume expansion, a value of less than 12% is considered to be very good, preferably the expansion should be less than 8%.

The gassing after partial discharge is good for values less than 12 ml, and preferably less than 8 ml, for both the gassing tests after 4½ hrs or 1 hr of discharge.

10 Comparison of Examples No. (1)-(9) with Examples No. (10)-(18) shows that the powders according to the invention have better corrosion resistance and expansion parameters than traditionally prepared powders. The compositions of the Examples No. (10), (14), (15) and (16), which do not yield acceptable results when prepared in the traditional way, have excellent results
15 when prepared according to the invention, as shown in Examples No. (1), (5), (6) and (7). Examples No. (20), (22)-(24) show that centrifugal atomisation is not yielding satisfactory results for zinc powders consisting of alloys other than the compositions claimed in the invention.

It has been noticed that the powder capacity of the powders prepared by
20 centrifugal atomisation in this experiment and used in LR-6 batteries is varying between 90 % and 110 % as compared to a standard powder used in these batteries nowadays, for instance the powder according to Example No. (12) above.

25 Experiment 2

In Experiment 2 a comparison is made between powders which were made exclusively by centrifugal atomisation but with different oxygen contents in the protective atmosphere. The other process parameters and the
30 test procedure of the LR-14 batteries using the powders are identical to Experiment 1. The results are presented in Table 2.

Table 2: Volume expansion of different centrifugally atomised powders

Ex. No.	Alloy powder additives (ppm)					O ₂ % by Volume	Volume expansion (%)
	In	Bi	Ca	Al	Pb		
(25)	200	100	-	100	54	2.5	3.0
(26)	150	150	-	-	40	2.0	5.6
(27)	200	100	-	100	54	5	12.3
(28)	150	150	-	-	40	air	23.6

5 The results of this experiment are the following:

- when the oxygen content in the protective atmosphere of the centrifugal atomising chamber is outside the limits of this invention, then the volume expansion measured becomes unacceptable, as is shown when comparing Examples No. (25) and (26), with (27) and (28).

10

Experiment 3

In Experiment 3 powders prepared by traditional gas jet atomisation under a protective atmosphere are compared with powders prepared by centrifugal atomisation under the same protective atmosphere. The procedure for the centrifugal atomisation is identical to the procedure in Experiment 1. The powders were tested in LR-6 batteries, which were discharged at a constant current of 1000 mA. A standard air atomised powder used in LR-6 batteries nowadays, i.e. the powder Example No. (12) from Table 1, was used as a reference. The discharge time to a residual voltage of 1.0 V for the different powders is expressed as a percentage of the discharge time to 1.0 V for the reference powder. The discharge time is a measure which expresses the capacity of the tested batteries. The results are given in Table 3 below.

Table 3: Discharge time of batteries prepared with centrifugally atomised vs. gas jet atomised powders

Ex. No.	Alloy powder additives (ppm)					(***)	O ₂ % by Volume	Discharge time (%)
	In	Bi	Ca	Al	Pb			
(29)	160	230	-	-	46	C	2.35	102
(30)	160	230	-	-	46	C	0.6	90
(31)	160	230	-	-	46	G	2.35	87
(32)	160	230	-	-	46	G	0.6	61

(**): 'C': centrifugal atomized powder; 'G': powder preparation by gas jet

5 atomisation

The results of Experiment 3 are the following:

- both discharge times for centrifugally atomised powders are within the claimed range of 90-110% of the discharge time of the standard powder. 2.35%

10 O₂ yields a better capacity than 0.6% O₂.

- both discharge times for the gas atomised powder are significantly lower than the discharge times of powders atomised centrifugally in gas with the same composition of the powder and of the protective atmosphere, and are less than 90%.

15

In Table 5 additional results for powders prepared by centrifugal atomisation according to the invention are given. They have been prepared and tested following the procedure of Experiment 1.

Table 5: Volume expansion of different centrifugally atomised powders

Ex. No.	Alloy powder additives (ppm)					O ₂ % by Volume	Volume expansion (%)
	In	Bi	Ca	Al	Pb		
(33)	250	250	150	-	-	0.6	3.3
(34)	500	110	-	35	-	0.6	1.9
(35)	500	110	-	35	-	1.35	2.5
(36)	500	110	-	35	-	1.6	2.1
(37)	500	110	-	35	-	2.1	6.7
(38)	500	110	-	35	-	2.6	7.6
(39)	150	230	-	-	-	1.6	5.5
(40)	200	100	-	100	-	1.6	4.0
(41)	200	100	-	100	-	2.6	2.9
(42)	150	230	-	-	-	0	5.6
(43)	150	230	-	-	-	2	7.3
(44)	200	100	-	100	40	2	2.7
(45)	150	230	-	-	38	2.45	6.7
(46)	150	230	-	-	55	0.25	5.0
(47)	200	100	-	100	40	3.5	3.7

CLAIMS

1. A centrifugal atomized zinc alloy powder for alkaline batteries consisting of either of
 - 5 (a) 0.005-2 % by weight of indium, and 0.005-0.2 % by weight of either one of Al and Bi, or
 - (b) 0.005-2 % by weight of indium, and 0.005-0.2 % by weight of Bi, and 0.001-0.5 % of either one or both of Al and Ca, or
 - 10 (c) 0.005-2 % by weight of either one or both of Bi and Al, and 0-0.5 % by weight of Pb, the remainder being zinc,and characterized in that the centrifugal atomising process is performed in a protective atmosphere, where the oxygen content is less than 4% by volume.
2. A centrifugal atomized zinc alloy powder according to claim 1, consisting of
 - 15 (a) 0.01-2 % by weight of indium, and 0.01-0.2 % by weight of either one of Al and Bi, or
 - (b) 0.005-2 % by weight of indium, and 0.01-0.2 % by weight of Bi, and 0.003-0.5 % of either one or both of Al and Ca, or
 - 20 (c) 0.01-2 % by weight of either one or both of Bi and Al, and 0-0.5 % by weight of Pb, the remainder being zinc.
3. A centrifugal atomized zinc alloy powder in alkaline batteries according to claim 1 or 2, characterized in that the oxygen content in the protective atmosphere is greater than 0 % by volume.
- 25 4. A centrifugal atomized zinc alloy powder in alkaline batteries according to claim 3, characterized in that the oxygen content in the protective atmosphere is between 0.2 % and 3.5% by volume.
5. An alkaline battery consisting of an anode, a cathode and an electrolyte, characterized in that the battery uses a centrifugal atomized zinc alloy
 - 30 powder according to one of the claims 1-4.
6. An alkaline battery according to claim 5, characterized in that the powder comprises metal cemented out of the electrolyte.
7. A process for the manufacturing of a zinc alloy powder for alkaline batteries , comprising the step of centrifugally atomising a zinc alloy
 - 35 consisting either of
 - (a) 0.005-2 % by weight of indium, and 0.005-0.2 % by weight of either one of Al and Bi, or

- (b) 0.005-2 % by weight of indium, and 0.005-0.2 % by weight of Bi, and 0.001-0.5 % of either one or both of Al and Ca, or
- (c) 0.005-2 % by weight of either one or both of Bi and Al, and 0-0.5 % by weight of Pb, the remainder being zinc, characterized in that the centrifugal atomising process is performed in a protective atmosphere, where the oxygen content is less than 4% by volume.
- 5 8. A process for the manufacturing of a zinc alloy powder for alkaline batteries, comprising the step of centrifugally atomising a zinc alloy consisting either of
- 10 (a) 0.01-2 % by weight of indium, and 0.01-0.2 % by weight of either one of Al and Bi, or
- (b) 0.005-2 % by weight of indium, and 0.01-0.2 % by weight of Bi, and 0.003-0.5 % of either one or both of Al and Ca, or
- (c) 0.01-2 % by weight of either one or both of Bi and Al, and 0-0.5 % by weight of Pb, the remainder being zinc, characterized in that the centrifugal atomising process is performed in a protective atmosphere, where the oxygen content is less than 4% by volume.
- 15 9. A process according to claims 7 or 8, characterized in that the oxygen content in the protective atmosphere is greater than 0 % by volume.
- 20 10. A process according to claims 7 to 9, characterized in that the oxygen content in the protective atmosphere is between 0.2 % and 3.5% by volume.

INTERNATIONAL SEARCH REPORT

International Application No

PCT/EP 00/00932

A. CLASSIFICATION OF SUBJECT MATTER

IPC 7 H01M4/42 C22C1/04 B22F9/10

According to International Patent Classification (IPC) or to both national classification and IPC

B. FIELDS SEARCHED

Minimum documentation searched (classification system followed by classification symbols)

IPC 7 H01M C22C B22F

Documentation searched other than minimum documentation to the extent that such documents are included in the fields searched

Electronic data base consulted during the international search (name of data base and, where practical, search terms used)

C. DOCUMENTS CONSIDERED TO BE RELEVANT

Category *	Citation of document, with indication, where appropriate, of the relevant passages	Relevant to claim No.
X	PATENT ABSTRACTS OF JAPAN vol. 013, no. 254 (E-772), 13 June 1989 (1989-06-13) & JP 01 052379 A (MITSUI MINING & SMELTING CO LTD; OTHERS: 01), 28 February 1989 (1989-02-28) abstract	1-10
X	PATENT ABSTRACTS OF JAPAN vol. 010, no. 228 (E-426), 8 August 1986 (1986-08-08) -& JP 61 064074 A (TOSHIBA BATTERY CO LTD), 2 April 1986 (1986-04-02) abstract	1-10
	-/--	

☒ Further documents are listed in the continuation of box C.

☒ Patent family members are listed in annex.

* Special categories of cited documents:

"A" document defining the general state of the art which is not considered to be of particular relevance

"E" earlier document but published on or after the international filing date

"L" document which may throw doubts on priority claim(s) or which is cited to establish the publication date of another citation or other special reason (as specified)

"O" document referring to an oral disclosure, use, exhibition or other means

"P" document published prior to the international filing date but later than the priority date claimed

"T" later document published after the international filing date or priority date and not in conflict with the application but cited to understand the principle or theory underlying the invention

"X" document of particular relevance; the claimed invention cannot be considered novel or cannot be considered to involve an inventive step when the document is taken alone

"Y" document of particular relevance; the claimed invention cannot be considered to involve an inventive step when the document is combined with one or more other such documents, such combination being obvious to a person skilled in the art.

"&" document member of the same patent family

Date of the actual completion of the international search

9 June 2000

Date of mailing of the international search report

19/06/2000

Name and mailing address of the ISA

European Patent Office, P.B. 5818 Patentlaan 2
NL - 2280 HV Rijswijk
Tel. (+31-70) 340-2040, Tx. 31 651 epo nl,
Fax: (+31-70) 340-3016

Authorized officer

Riba Vilanova, M

INTERNATIONAL SEARCH REPORT

International Application No

PCT/EP 00/00932

C.(Continuation) DOCUMENTS CONSIDERED TO BE RELEVANT

Category *	Citation of document, with indication, where appropriate, of the relevant passages	Relevant to claim No.
X	PATENT ABSTRACTS OF JAPAN vol. 008, no. 069 (M-286), 31 March 1984 (1984-03-31) & JP 58 217608 A (TOUYOU KINZOKUKO KK; OTHERS: 01), 17 December 1983 (1983-12-17) abstract	1-10
A	WO 94 19502 A (UNION MINIERE SA ; STRAUVEN IVAN A J (BE); MEEUS MARCEL L (BE)) 1 September 1994 (1994-09-01) cited in the application * whole document * page 3, line 14 - line 31 examples claims	1-10
A	US 5 082 622 A (STRAUVEN YVAN ET AL) 21 January 1992 (1992-01-21) cited in the application column 1, line 49 - column 2, line 24; table claims	1-10
A	WO 96 06196 A (UNION MINIERE SA ; STRAUVEN IVAN A J (BE); MEEUS MARCEL L (BE)) 29 February 1996 (1996-02-29) page 3, line 1 - line 18 examples claims	1-10
A	WO 96 07765 A (UNION MINIERE SA ; STRAUVEN IVAN A J (BE); MEEUS MARCEL L (BE)) 14 March 1996 (1996-03-14) page 3, line 14 - line 29 examples claims	1-10

INTERNATIONAL SEARCH REPORT

Information on patent family members

Int. ional Application No

PCT/EP 00/00932

Patent document cited in search report	Publication date	Patent family member(s)	Publication date
JP 01052379 A	28-02-1989	NONE	
JP 61064074 A	02-04-1986	JP 1687835 C JP 3055023 B	11-08-1992 22-08-1991
JP 58217608 A	17-12-1983	JP 1615139 C JP 60009082 B	30-08-1991 07-03-1985
WO 9419502 A	01-09-1994	BE 1007443 A AU 6141194 A CA 2153330 A CN 1118610 A,B DE 69424157 D EP 0686207 A JP 8510010 T LT 1881 A,B	04-07-1995 14-09-1994 01-09-1994 13-03-1996 31-05-2000 13-12-1995 22-10-1996 25-10-1994
US 5082622 A	21-01-1992	BE 1003415 A AU 625011 B AU 6588290 A CA 2029436 A EP 0427315 A JP 3173731 A NO 904857 A	17-03-1992 25-06-1992 16-05-1991 11-05-1991 15-05-1991 29-07-1991 13-05-1991
WO 9606196 A	29-02-1996	BE 1008626 A AU 3383895 A CN 1164874 A,B DE 69505992 D DE 69505992 T EP 0777754 A ES 2126929 T JP 10504679 T	04-06-1996 14-03-1996 12-11-1997 17-12-1998 29-07-1999 11-06-1997 01-04-1999 06-05-1998
WO 9607765 A	14-03-1996	BE 1008715 A AU 3472695 A	02-07-1996 27-03-1996